



1501 West 178<sup>th</sup> Street | Gardena, CA. 90248  
310-767-7812 | 800-359-5679 | fax: 310-767-7836  
[info@matsui-color.com](mailto:info@matsui-color.com) | [www.matsui-color.com](http://www.matsui-color.com)

## WW0072 PC White 70

### Technical Data Sheet

- **Wet Ink Tack** | Low
- **After Flash Tack** | Low
- **Printability** | Excellent
- **Surface Appearance** | N/A
- **Opacity/Viscosity** | N/A
- **Bleed Resistance** | N/A
- **Gel Point/Flash Time** | N/A
- **Fusion Temperature** | N/A
- **Squeegee Hardness** | N/A
- **Squeegee Blade** | N/A
- **Squeegee Angle** | N/A
- **Squeegee Speed** | N/A
- **Underlay** | N/A
- **Emulsion** | N/A
- **Mesh Count** | N/A
- **Thinner** | RV Additive
- **Thickener** | Thickener B
- **Storage** | 65°F to 95°F (18°C to 35°C). Avoid direct sun.
- **Cleanup** | Water and mild soap or detergent
- **Color Range** | White
- **Substrate Type** | N/A
- **Substrate Color(s)** | N/A

### Description

**PC White 70** is a white pigment can be mixed with Neo Pigment to create desired tone.

### Features

- Easy to mix and print
- Can be blended with **Neo Pigments** up to 20% to achieve pastel colors
- Excellent printability with no viscosity modifications
- Extremely soft hand feel that PVC inks cannot achieve
- Is "PVC Free"

### Application

Please follow the application for the base mixing the **PC White 70**

### Special Recommendations

**PC White 70** should be mixed in clean vessels using clean mixing blades and utensils. Any contamination from other ink sources or non-approved additives could make **PC White 70** test positive for restricted PVC's.

- **PC White 70** can be dry cleaned or ironed
- Use Retarder MG 1-5% to help with open time in the screen
- Use Fixer WF-N 1-5% to help with wash fastness
- Use Softener MG 1-4% to help penetrate in to the garment
- Use Thickener B .25-1% to help thicken the ink
- Use RV Additive 1-3% to reduce viscosity