



1501 West 178<sup>th</sup> Street | Gardena, CA. 90248  
310-767-7812 | 800-359-5679 | fax: 310-767-7836  
[info@matsui-color.com](mailto:info@matsui-color.com) | [www.matsui-color.com](http://www.matsui-color.com)

## WW0203 Brite Discharge Super 75 White

### Technical Data Sheet

- **Wet Ink Tack** | Low
- **After Flash Tack** | Low
- **Printability** | Excellent
- **Surface Appearance** | Matte
- **Opacity/Viscosity** | Low/Low
- **Bleed Resistance** | None
- **Gel Point/Flash Time** | 160°F (71°C)/decreases with deposit thickness
- **Fusion Temperature** | 320°F (160°C)
- **Squeegee Hardness** | Medium
- **Squeegee Blade** | Sharp
- **Squeegee Angle** | 45 degrees to screen
- **Squeegee Speed** | Medium
- **Underlay** | N/A
- **Emulsion** | Direct or indirect
- **Mesh Count** | 110-305 mc in (43-120 mc cm)
- **Thinner** | RV Additive
- **Thickener** | Thickener B
- **Storage** | 65°F to 95°F (18°C to 35°C). Avoid direct sun.
- **Cleanup** | Water and mild soap or detergent
- **Color Range** | Clear
- **Substrate Type** | Cotton
- **Substrate Color(s)** | Light, Medium and Dark Fabrics

### Description

**Brite Discharge Super 75 White** is a blended discharge white that produces an opaque discharge white with excellent printability.

### Features

- Easy to mix and print
- Can be blended with **Neo Pigments** up to 15% to achieve pastel colors
- Economical version of **Brite Discharge White**
- Excellent printability with no viscosity modifications
- Extremely soft hand feel that PVC inks cannot achieve
- CPSIA and HR4040 Compliant
- Is "PVC Free"

### Application

Print through mesh up to 160 mc in (63 mc cm) when cured at 320°F (160°C), **Brite Discharge Super 75 White** produces the softest prints achievable in textile screen printing today.

### Special Recommendations

**Brite Discharge Super 75 White** should be mixed in clean vessels using clean mixing blades and utensils. Any contamination from other ink sources or non-approved additives could make **Brite Discharge Super 75 White** test positive for restricted PVC's.

- **Brite Discharge Super 75 White** can be dry cleaned or ironed
- Use **Retarder MG 1-5%** to help with open time in the screen
- Use **Fixer WF-N 1-5%** to help with wash fastness
- Use **Softener MG 1-4%** to help penetrate in to the garment
- Use **Thickener B .25-1%** to help thicken the ink
- Use **RV Additive 1-3%** to reduce viscosity