



1501 West 178th Street | Gardena, CA. 90248
310-767-7812 | 800-359-5679 | fax: 310-767-7836
info@matsui-color.com | www.matsui-color.com

DA0115 Digiac Digital Top Coat

Technical Data Sheet

- **Wet Ink Tack** | Low
- **After Flash Tack** | Low
- **Printability** | Excellent
- **Surface Appearance** | Clear
- **Opacity/Viscosity** | Low/Low
- **Bleed Resistance** | None
- **Gel Point/Flash Time** | 160°F (71°C)/decreases with deposit thickness
- **Fusion Temperature** | 320°F (160°C)
- **Squeegee Hardness** | Medium
- **Squeegee Blade** | Sharp
- **Squeegee Angle** | 15 degrees to screen
- **Squeegee Speed** | Medium
- **Underlay** | N/A
- **Emulsion** | Direct or indirect
- **Mesh Count** | 110-230 mc in (43-90 mc cm)
- **Thinner** | RV Additive
- **Thickener** | Thickener B
- **Storage** | 65°F to 95°F (18°C to 35°C). Avoid direct sun.
- **Cleanup** | Water and mild soap or detergent
- **Color Range** | Clear
- **Substrate Type** | Most
- **Substrate Color(s)** | Medium and Dark Fabrics

Description

Digiace Digital Top Coat is a clear overprint/sealer screen ink used to encapsulate and protect the digital. Recommended for use with low resin digital inks.

Features

- Ready for use
- Excellent printability with no viscosity modifications
- Extremely soft hand feel that PVC inks cannot achieve
- Is “PVC Free” and environmentally safe

Application

Print after digital print through screen mesh up to 230 in (90 cm) with a recommend dryer temperature of 320°F (160°C) for 2-3 minutes, **Digiace Digital Top Coat** produces the softest prints achievable in textile hybrid screen printing today.

Special Recommendations

Digiace Digital Top Coat should be mixed in clean vessels using clean mixing blades and utensils. Any contamination from other ink sources or non-approved additives could make **Digiace Digital Top Coat** test positive for restricted PVC's.