



MPC125

Epoxy Primers

274 808SP/ Black
274 908SP/ White

Matthews Epoxy Primers are corrosion resistant primers that provide excellent adhesion to many types of substrates and can also be used in 3.5 VOC compliant areas.

Combine the white epoxy with the black to create a wide range of gray shades to compliment the topcoat.



Features:

- Low VOC technology Environmentally friendly, meets 3.5 VOC regulations
- Chromate-free..... Meets EPA regulations for chromate restrictions
- Available in Black and White..... Combine together for any shade of gray
- Topcoat with any Matthews Acrylic Polyurethane finishes..... Versatile, multi-purpose
- Compatible over various substrates..... For multiple applications, fewer products to stock
- Brush and roll capability For use in areas where air spraying is prohibited
- Epoxy technology Excellent corrosion resistance, superior adhesion to substrate
- Excellent filling properties..... Capable of hiding minor metal substrate defects
- Easy mix ratio Less time mixing
- 24 hours topcoat window No sanding required prior to topcoating within window
- Anti-corrosion properties..... Provides excellent corrosion protection

Benefits:

Compatible Surfaces:

274 808SP and 274 908SP Epoxy Primers may be applied over properly prepared:

Steel	Aluminum	Masonry
Blasted steel	Fiberglass	Wood
Carbon steel	Previously painted surfaces	
Galvanized steel	Body filler	

Associated Products:

Catalyst	Exempt MAP Reducer (for 3.5 VOC)
274 909SP Epoxy Hardener	6370SP Cool temperature, 60 - 75°F (16 - 24°C)
	6371SP Warm temperature, 70 - 85°F (21 - 29°C)
	6372SP Hot temperature, 80°F (27°C) & above

Note: if 3.5 VOC is not required, any Matthews conventional or low VOC reducer can be used.

274 808SP/ Black, 274 908SP/ White

Directions for Use

Surface Preparation: Substrate should be prepared according to Matthews Substrate Preparation Guide prior to primer application.

Mix Ratio:



Mix Ratio for Spraying (by volume)

274 808SP / White	274 908SP / Black	274 909SP	Reducer**
3 parts*	1 part	1 part	

*Any combination of black and white may be mixed together to make gray prior to catalyzing and reducing.

To achieve various shades of gray the table below may be used as a guideline.

	274 908SP (White)	274 808SP (Black)
White	100%	-
Light Grey	75%	25%
Medium Grey	50%	50%
Dark Grey	25%	75%
Black	-	100%

**Choose VOC MAP reducer

For 3.5 VOC:

- 6370SP Cool temperature, 60 - 75°F (16 - 24°C)
- 6371SP Warm temperature, 70 - 85°F (21 - 29°C)
- 6372SP Hot temperature, 80°F (27°C) & above
- NOTE: Larger jobs may require a hotter temperature reducer.

If 3.5 VOC is not required, any Matthews conventional or low VOC reducer can be used.

- All components should be mixed thoroughly before using
- Strain material after mixing



Pot Life: 4 hours

Pot-life is the amount of time before spray viscosity doubles. These are estimates based on lab results at 50% relative humidity, 70°F/21°C—results will vary based on application conditions, reducer selection, and accelerator choice.

Note: mix no more product than can be used within pot life.

Additives:



None

Spray Set Up:



Air Pressure: Conventional: 40 - 50 psi at the gun*
 HVLP: 10 psi at the cap*

* Refer to spray gun manufacturer recommendations for inlet pressure.



Pressure Pot Fluid Delivery: 8 - 12 Fluid Ounces per Minute



Gun Set Up: Siphon Feed: 1.3 - 1.5 mm 0.051 - 0.059 fluid tip
 HVLP: 1.3 - 1.5 mm 0.051 - 0.059 fluid tip
 Pressure Pot: 1.0 - 1.2 mm 0.039 - 0.047 fluid tip

274 808SP/ Black, 274 908SP/ White

Directions for Use

Application:



Apply:

Apply one to two full wet coats, allowing proper flash time* between coats.
Apply additional coats as necessary to achieve total dry film thickness.
***Flash times will vary dependent upon film thickness, temperature, solvent selection, spray gun set-up, application, etc.**

Recommended
Film Thickness:

	One Coat Application	Two Coat Application
Wet Film Thickness (WFT)	2.0 - 3.0 mils	4.0 - 6.0 mils
Dry Film Thickness (DFT)	0.8 - 1.2 mils	1.6 - 2.4 mils

Caution: All 2-component crosslinking slows significantly at temperatures below 60°F or 16°C. Never spray or subject freshly painted coatings to these conditions or loss of gloss, decreased durability and improper curing can occur.

Estimated Drying Times:



Air-Dry @ 50% Relative Humidity, 70°F/21°C
Dust Free 20 - 30 minutes
Dry to Touch 25 - 35 minutes
Dry to Handle 30 - 45 minutes
Dry to Topcoat 30 minutes - 24 hours (max)*

*After 24 hours, sand with a 220-400 grit dry, or equivalent sanding pad. Do not sand below minimum dry film thickness, otherwise reprime before topcoating.

Equipment Cleaning:

Clean equipment promptly with lacquer thinner or equivalent cleaning solvent.

Note: Do not leave mixed material in equipment.

Technical Data:

3.5 VOC Information

VOC Actual RTS	2.64 lbs/gal
VOC Actual RTS	316 g/L
VOC Regulatory (less water less exempt) RTS	3.3 lbs/gal
VOC Regulatory (less water less exempt) RTS	395 g/L

Above 3.5 VOC* Information

VOC Actual RTS	4.07 lbs/gal
VOC Actual RTS	487 g/L
VOC Regulatory (less water less exempt) RTS	4.07 lbs/gal
VOC Regulatory (less water less exempt) RTS	487 g/L

*>3.5 VOC calculations when using 45 290SP as an example

For complete VOC information, visit MatthewsPaint.com > Quick Links > VOC Data

Performance Characteristics

Volume solids (RTS)	42.8%
Theoretical Coverage (1 mil @ 100% transfer efficiency)	685 sq.ft./RTS gal
Application Conditions - Temperature	60°F (16°C) Minimum 100°F (38°C) Maximum
Application Conditions - Relative Humidity	85% maximum 5° above dew point

274 808SP/ Black, 274 908SP/ White

Epoxy Primers

Important: The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

See Safety Data Sheet and Labels for additional safety information and handling instructions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION - US (412) 434-4515; CANADA (514) 645-1320; Mexico 01-800-00-21-400
Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to Matthews Paint. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does Matthews Paint warrant freedom from patent infringement in the use of any formula or process set forth herein. If you require technical assistance, please call us toll-free 800/323-6593.



The World's Finest Coating For Architectural Signage

760 Pittsburgh Drive
Delaware, OH 43015
Toll Free: 800/323-6593
Toll Free FAX: 800/947-0377