



▶ DPF 4600GLX/MLX Vinyl Film

High Performance Digital Film with X-Scape Technology®

DPF 4600GLX/MLX is constructed of a 3.2-mil (80 micron) white gloss or matte high performance calendared film with a tinted, clean removing, repositionable adhesive system. The repositionable light gray adhesive allows for easy installation while ensuring enough opacity for covering up existing graphics or dark substrates. The Low Profile X-Scape Technology provides installers the benefit of a bubble-free installation combined with a smooth printed surface that doesn't show the pattern through the print. DPF 4600GLX/MLX works great for your multipurpose signage needs. DPF 4600GLX/MLX is rated for outdoor durability up to 7 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Printable on Eco-Solvent, Solvent, Latex and UV printers
- Ideal for interior & exterior intermediate signage
- Great for partial vehicle wraps with flat & simple curves
- Recommended overlaminates: Series 3220, Series 3210, Series 3170, Series 3410* or Series 3420

* Only available in Europe and the Middle East.



PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	80 to 90 Gloss Units (Gloss) 10 to 15 Gloss Units (Matte)	
THICKNESS	Micrometer, Federal Bench Type	3.2-mil (80 micron)	
TENSILE STRENGTH	Tensile Tester 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s); web direction	≥ 14 lb/in	≥ 2.5 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 190%	
SHELF LIFE (IN BOX)	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	60°F to 80°F	15°C to 27°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-20°F to 150°F	-29°C to 65°C
DIMENSIONAL STABILITY	158°F (70°C), 48 hour	15-mil	0.38 mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	≥ 3.9 lb/in	≥ 0.70 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	70 g/2 in	14 g/cm

NOTE: Recommended post-heat surface temperature of vinyl installed: 200°F to 220°F (95°C to 105°C). Post-heat must be applied gradually and approximately 5" from the film. Standard Terms & Conditions Apply

USE & APPLICATION

DPF 4600GLX/MLX will resist weathering best when applied to vertical or upper outboard angles. Horizontal angles, such as hood and auto roof surfaces, will deteriorate more quickly than vertical. This is due to increased exposure to sun and moisture, as well as high deposition of dirt and atmospheric contaminants. Actual horizontal weathering will be dependent on maintenance, location and elemental exposure. Use heat and/or chemical when removing image from vehicle (see Installer Handbook for details).

APPLICATION	RECOMMENDED	NOT RECOMMENDED	OVERLAMINATE(S)
VEHICLE/FLEET DECALS	X		SERIES 3220, SERIES 3210, SERIES 3170, SERIES 3410 OR SERIES 3420
FLAT VEHICLE SIDES	X		SERIES 3220, SERIES 3210, SERIES 3170, SERIES 3410 OR SERIES 3420
SIMPLE CURVES	X		SERIES 3220, SERIES 3210, SERIES 3170, SERIES 3410
DEEP CHANNELS		X*	
COMPLEX CURVES		X	
RIVETS		X ⁺	
MULTI-PURPOSE FLAT APPLICATIONS	X		SERIES 3220, SERIES 3210, SERIES 3170, SERIES 3410 OR SERIES 3420
MEDIUM-TERM STATIC SIGNAGE	X		SERIES 3220, SERIES 3210, SERIES 3170, SERIES 3410 OR SERIES 3420

*When wrapping curves and channels with DPF 4600GLX/MLX, it is recommended the product be draped and not stretched into areas with channels.
⁺Can be applied on low profile rivets. Please note that rivets vary in shape and size so tenting may appear.

GLOSSARY OF APPLICATION TERMS

- Simple Curves:** Defined as a slight stretch to the film in one direction (example: the side vehicle).
- Complex Curves:** Defined as extensive stretching (with or without heat) of material in multiple directions (example: bumpers).
- Deep Channel:** Channels in excess of a quarter inch in depth that require a “bridge and stretch” method for application.

TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:


All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller’s and manufacturer’s only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.


April 2019

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA

EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

 800 232 7161/+1 714 985 6300

 +31 70 354 4311

 800 329 2756

 +31 70 355 7721

arlon.com