Rutland™ LB0266 CHILL LB LC BARRIER BASE





Rutland™ LB0266 Chill LB LC Barrier Base is an underbase product created to block unstable garment dyes from migrating into top colors or whites on the very worst dyed fabrics or poly garments that are dye sublimated with patterns such as Camo and Digi-Camo. Chill LB LC Barrier Base cures as low as 250°F (121°C) when printing on polyester garments produced with unstable dyes or are prone to shrinkage when exposed to heat.

Highlights Printing Tips Lower cure temperatures allow for better control on fabrics that may shrink Adjust flash cure temperature and dwell time so ink is just dry to touch. 0 or distort under higher temperatures Avoid excessive flash temperatures to protect fabric and migration of dyes. Works well on manual or automatic presses Use 86–110t/in (34-43t/cm) mesh screens for best performance and opacity Shears down quickly to a creamy, smooth body For printing under a white or color over-print, it is typical to print two strokes of Chill Barrier Base, flash until dry to the touch, and then print white or colors over the barrier under base, flashing as needed. Excellent bleed resistance at a wide temperature range: 250-320°F Adjust your print parameters to allow ink to clear fully on the second stroke, Can cause energy savings and cooler operating temperatures using medium-to-low pressure for best dye blocking and opacity. As this ink shears down, less pressure will be required. Adjust accordingly. Curing is a time and temperature process. Using a lower temperature at a lower belt speed will provide the best result without damaging the fabric. Compliance Sustainability A behavior for high-opacity low cure inks is to "body-up" or gain viscosity when at rest. Be sure to "pre-shear" or agitate this ink before use to achieve Non-phthalate optimal flow before printing. Be careful to not use high-speed drills or similar equipment that will create friction-heat that can cause the ink to begin to cure. Store ink buckets off of cold floors to reduce pre-shear time. Internationally compliant Reduced **Energy Use** Visit https://www.avientspecialtyinks.com/ services/compliance-support **Precautions** The information provided in this document is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications

Recommended Parameters



Fabric Types

100% polyester, poly blends



Flash & Cure

Flash: 150° F (66° C)

Cure: 250°-320° F (121° -160° C)



Clean Up

Non-phthalate press wash



Mesh

Count: 86-110t/in (34-43t/cm)

Tension: 18-35n/cm3



Pigment Loading

N/A



Health & Safety

Find SDS information here: www.avient.com/resources/safety-data-sheets or contact your local CSR



Squeegee

Durometer: Medium: 60-70, 60/90/60

Profile: sharp, square

Stroke: 2 stroke, medium speed

Angle: 10° -20°



Additives



Standard Emulsion Off Contact: 1/16" (2mm) Emulsion Over Mesh: 15-20%



Storage

65°-90° F (18°-32° C) Avoid direct sunlight. Use within one year of receipt. Keep container well sealed.



AVIENT SPECIALTY INKS

V5.00 (Modified: 09/10/2024)

2024. Avient Corporation, Avient makes no representations guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTARII ITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.