PRODUCT INFORMATION BULLETIN

LC0540 CHILL LC **COTTON MIXING BASE**

printing on 100% Cotton or over a Chill LC low bleed underlay when printing on poly/cotton blends.

Rutland

Highlights Printina Tips Mix with Rutland[™] C3 colors When blended according to formulations, colors will be semi-opaque \bigcirc 0 Adjust flash cure temperature and dwell time so ink is just dry to touch. Semi-opaque colors 0 \bigcirc Depending on flash unit, a 2 - 3 second flash is adequate Flex cure temp from 270°F - 320°F (132°C - 160°C) LC0540 Chill LC Cotton Mixing Base is not a low-bleed ink, when printing on \bigcirc fabrics that are prone to bleed underbase with Chill LC LB Tidy White, Chill LC Polywhite and/or Chill LC Barrier Grey Wet-on-wet printing at high production speeds O 0 Exhibits good color retention in high-speed wet-on-wet production with Matte finish exceptional resistance to build up 0 Printers should always test the ink on their fabric under their process 0 conditions before printing production runs Compliance Non-phthalate 0 Internationally compliant O Visit www.rutlandinc.com for more information Precautions The information provided in this document is given in good faith and does not 0 release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications **Recommended Parameters Fabric Types** Flash & Cure Clean Up 100% cotton Flash: 220°F (105°C) Unused ink will need to be disposed of Cure: 270°F (132°C) Entire ink film responsibly. Standard plastisol cleaners, press wash, or ink degradant **Health & Safety** Mesh **Pigment Loading** Find SDS information here: Count: 86-305 t/in (34-120 t/cm) Maximum 25% C3 www.avient.com/resources/safety-data-Tension: 25-35n/cm2 sheets or contact your local CSR 2022, Avient Corporation, Avient makes no representations guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for Additives Squeegee particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work Durometer: 60/90/60, 70/90/70, 60-90 **K2912 VISCOSITY BUSTER LC** with small-scale equipment which may not provide a reliable Profile: Square, Sharp indication of performance or properties obtained or obtainable on Stroke: Medium flood, Medium-Fast stroke larger-scale equipment. Values reported as "typical" or stated Angle: 10°-15° without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no Stencil Storage warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application 2 over 2 65°-90°F (18°-32°C) You have the responsibility to conduct full-scale end-product Off Contact: 1/16" (2mm) Avoid direct sunlight. performance testing to determine suitability in your application, and Emulsion Over Mesh: 15-20% Use within one year of receipt. you assume all risk and liability arising from your use of the Keep container well sealed. information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR

Rutland™ LC0540 Chill LC Cotton Mixing Base is formulated as a press-ready flex cure base for mixing colors using C3 Color Boosters and

V1.00 (Modified: 06/09/2022)

PURPOSE, either with respect to the information or products

permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

reflected by the information. This literature shall NOT operate as

AVIENT SPECIALTY